



Reinforcement Technical Datasheet

All Lotrak® reinforcing geotextiles and geogrids are designed to provide effective reinforcement to weak sub grades, absorbing stresses caused by heavy traffic.

Dependent on the specific site requirements, Lotrak® reinforcing geotextiles act as the reinforcement, separator and filtration membrane to provide all functions in one geotextile. This eliminates the need for multiple products and offers clear cost benefits.

Where there is a requirement for individual membranes, Lotrak® reinforcing geotextiles or the range of Lotrak® biaxial geogrids provide good ground stabilisation and reinforcement.

Features

- ^ The high strength and with low elongation of Lotrak® provides effective ground reinforcement
- ^ The aperture design of Lotrak® geogrids enables aggregate materials to interlock and encourages load dispersal
- ^ Lotrak® geogrids are manufactured under ISO Quality Management and the Construction Products Regulation

Benefits

- ^ Superior Reinforcement
- ^ High tensile strength
- ^ Superior separation
- ^ Excellent Soil & Aggregate Confinement
- ^ Cost Effective Design Component



TEST	STANDARD		25R	50R	70R	20/20S	30/30S	40/40S	30/30L
Tensile Strength (kN/m)	EN 10319	MD	26	52	74	20	30	40	30
		CD	26	52	72	20	30	40	30
Tensile Strength at 2% strain (%)	EN 10319	MD	-	-	-	7	10	14	10
		CD	-	-	-	8	10	14	9
Tensile Strength at 5% strain (%)	EN 10319	MD	16	25	55	15	21	25	21
		CD	16	45	55	17	23	29	20
Elongation at max. load (%)	EN 10319	MD	9	11	9	12	12	10	10
		CD	9	8	7	9	9	9	9
CBR Puncture Resistance (N)	EN ISO 12236		3200	6000	9200	-	-	-	-
Cone Drop Penetration (mm)	EN 918		12	8	6	-	-	-	-
Pore size 90% finer than (microns)	EN ISO 12956		270	210	240	-	-	-	-
Grid Opening Size (mm)			-	-	-	40x40	40x40	40x40	60x60
Water Permeability (x 10 ⁻³) (m/sec)	EN ISO 11058		10	14	18	-	-	-	-
Effect of UV Light	The polypropylene (PP) used contains a UV inhibitor								
Roll Size (m)		Width	5.0	5.0	5.0	3.95	3.95	3.95	3.95
		Length	100	100	100	50	50	50	50



All products are manufactured under BS EN ISO 9001.

Don & Low reserves the right to change specifications or other product information. Don & Low accepts no responsibility or liability for information provided by third parties. No warranties, express or implied, are offered regarding the suitability of any product for your use, as site conditions and customer requirements vary. Should you require further information, please contact us. Products are sold subject to the seller's terms and conditions of sale. No warranty or immunity is offered against infringement of patents or other intellectual property rights.

©Don & Low Limited, 2018. The intellectual property in the products is owned and protected by Don & Low or its licensors.