

Technical Datasheet

Meltblown TPU Apparel fabrics are soft to the touch, durable and breathable, which makes it ideally suited for performance wear applications. TPU (Thermoplastic Polyurethane) has natural water repellence, which as a nonwoven fabric gives the feature of low liquid absorption and quick drying.

	Test Method	Meltblown TPU Apparel							
Fabric weight (g/m²)	NWSP 130.1	50	55	80*	85	100	150	200	
Tensile Strength (N)	NWSP 110.4	MD	30	35	73	75	80	135	170
		CD	20	30	44	50	55	90	135
Elongation (%)	NWSP 110.4	MD	200	290	320	325	325	365	380
		CD	200	350	350	355	335	355	380
Air permeability (l/m²/s)	NWSP 070.1	400	550	225	250	220	140	93	
Thickness (mm)	NWSP 120.1	0.29	0.26	0.26	0.33	0.44	0.57	0.63	
Water Vapour Permeability		640 g/m ² . 24hr				WVP Index 97.3 %			

* compacted - surface bonded for improved wear resistance.

Customer Advice

Don & Low Ltd do not recommend that Meltblown TPU Apparel be used in any category of medical device or in any food contact application. Other grades of TPU, suitable for these applications, are available and enquiries should be sent to enquiries@donlow.co.uk. This fabric is a development product that has been successfully trialled in limited quantities on our production equipment. All dimensions and capacities quoted are approximate and the values provided are either based on theoretical data or a limited number of tests and should not be read as a final specification. To approve this as a full production grade and integrate it into our ISO 9001 system there are a number of steps that may still need to be taken. This could involve optimisation of process conditions or inclusion of a new raw material on our approved material lists. Additional trials may be necessary prior to product being approved. No commercial orders for this fabrics can be taken while it remains a development grade. Development samples older than 12 months may require re-evaluation as raw materials may no longer be available.



Thermoplastic Polyurethane is recyclable. Mechanical recycling is the primary option, depending on the requirements of the application and the intended article specification. It can also be valorised for energy recovery, its high calorific value is around 29 Mj/kg. Polyurethane is neither biodegradable nor compostable.

Don & Low reserves the right to change specifications or other product information. Don & Low accepts no responsibility or liability for information provided by third parties. No warranties, express or implied, are offered regarding the suitability of any product for your use, as site conditions and customer requirements vary. Should you require further information, please contact us. Products are sold subject to the seller's terms and conditions of sale. No warranty or immunity is offered against infringement of patents or other intellectual property rights.

©Don & Low Limited, 2024. The intellectual property in the products is owned and protected by Don & Low or its licensors.