

Technical Datasheet

Lotrak[®] 200 is a mechanically bonded nonwoven geotextile which withstands the use of larger varieties of granular materials whilst retaining an effective filtration capability. Lotrak[®] 200 is approved by Network Rail (Certificate of Acceptance PA05/06066) for drainage applications such as pipe or trench wrap and conforms to NR/SP/TRK/010 'Geotextiles'. (PADS Number: 057/101450).

TEST	STANDARD		Lotrak [®] 200
Tensile Strength (kN/m)	EN ISO 10319	MD	18
		CD	18
Elongation at max. load (%)	EN ISO 10319	MD	50
		CD	50
CBR Puncture Resistance (N)	EN ISO 12236		2900
Cone Drop Penetration (mm)	EN ISO13433		18
Pore size 90% finer than (microns)	EN ISO 12956		70
Water Permeability VI _{H50}	EN ISO 11058		0.080
Water Flow Rate (l/m ² /sec)	EN ISO 11058		80
Effect of UV Light	The polypropylene (PP) used contains a UV inhibitor		
Roll Size (m)			4.5 x 100

All products are manufactured under BS EN ISO 9001.

Don & Low reserves the right to change specifications or other product information. Don & Low accepts no responsibility or liability for information provided by third parties. No warranties, express or implied, are offered regarding the suitability of any product for your use, as site conditions and customer requirements vary. Should you require further information, please contact us. Products are sold subject to the seller's terms and conditions of sale. No warranty or immunity is offered against infringement of patents or other intellectual property rights.

©Don & Low Limited, 2024. The intellectual property in the products is owned and protected by Don & Low or its licensors.

