

## Technical Information

Proshield® is an advanced self-adhesive, vapour-permeable air barrier membrane designed to provide superior airtightness, moisture management, and ease of installation for modern construction projects. Manufactured by Don & Low, Proshield® ensures high-performance protection while optimizing energy efficiency across walls and floors.

With its Class B-s1,d0\* fire resistance, W1 water resistance, and high tensile strength, Proshield® ensures a level of durability that you can rely on for walls and floors. Its high vapour permeability prevents condensation, enhancing building longevity. Proshield® is available with a full range of tapes for airtight detailing and custom branding options for tailored solutions.

Proshield® conforms to the Construction Products Regulation (EU Regulation No. 305/2011) and is manufactured under control of an ISO 9001 quality management system.

TEST	METHOD	Proshield®						
Product Code		FNC 270						
Mass Per Unit Area with release liner (g/m <sup>2</sup> )	EN 1849-2	270						
Mass Per Unit Area without release liner (g/m <sup>2</sup> )		220						
Thickness with Release Liner (mm)	EN 1849-2	0.68						
Thickness without Release Liner(mm)		0.66						
Water Penetration Resistance (W1)	Method A of EN 1928 : 2000 (modified by EN 13859-2: 2014)	Pass						
Resistance to penetration of Air	EN 12114	< 0.01 m <sup>3</sup> /m <sup>2</sup> .h.50Pa						
Water Vapour Resistance (Sd)	EN ISO 12572	0.098m						
Tensile Strength (N)	EN 12311-1 (Modified by Annex A of EN 13859-2 : 2014)	Before ageing	<b>MD</b>	400	(-80)	<b>CD</b>	260	(-50)
		After ageing	<b>MD</b>	340	(-80)	<b>CD</b>	220	(-50)
Elongation (%)	EN 12311-1 (Modified by Annex A of EN 13859-2 : 2014)	Before ageing	<b>MD</b>	50	(-20)	<b>CD</b>	70	(-22)
		After ageing	<b>MD</b>	40	(-20)	<b>CD</b>	60	(-22)
Tear Resistance (N)	EN 12310-1 (Modified by Annex B of EN 13859-2 : 2014)		<b>MD</b>	190	(-50)	<b>CD</b>	190	(-60)
Dimensional Stability (%)	EN 1107-2		<b>MD</b>	+0.02		<b>CD</b>	+0.40	
Flexibility at low temperature	EN 1109	No cracking at -40°C						
Reaction to Fire Test Results*	BS EN 13501-1:2018	Class B, s1, d0	Calcium Silicate, Fibre Cement Board					
		Class F	Free standing					

\* Class B, s1, d0 Fire Classification achieved with either Calcium Silicate or Fibre Cement Board backing. Other substrates provide a lower fire classification.

**Conditions applicable to the end use of the product:** Rolls should be stored flat on a clean, level surface and kept under cover. Once the membrane is applied to the substrate, the primary covering should be installed within three months.

**Method of Installation:** Please refer to installation guide lines for detailed instructions.

Don & Low reserves the right to change specifications or other product information. Don & Low accepts no responsibility or liability for information provided by third parties. No warranties, express or implied, are offered regarding the suitability of any product for your use, as site conditions and customer requirements vary. Should you require further information, please contact us. Products are sold subject to the seller's terms and conditions of sale. No warranty or immunity is offered against infringement of patents or other intellectual property rights.

©Don & Low Limited, 2025. The intellectual property in the products is owned and protected by Don & Low or its licensors.

Don & Low Ltd, Glamis Road, Forfar, Angus, DD8 1FR, Scotland, UK

**Sales** Tel: +44(0)1307 452200 email: enquiries@donlow.co.uk

**Technical** Tel: 0808 169 4444 email: membranes@donlow.co.uk • [www.donlow.co.uk](http://www.donlow.co.uk)